

SPEEDPAK SERIES	Physical Properties - Cured		Typical properties - Liquid							
	CUBIC IN PER LB	COLOR	COMPONENT A*B*MIXED	VISCOSITY (CPS)	SPECIFIC GRAVITY	HAZARD	COMPONENT BY VOLUME	A*B MIXING BY WEIGHT	WORK LIFE	CURE TIME
SPEEDPAK	23.04 IN	LT YELLOW	8.88 LB	72 CPS	1.13	NON-H	100A-100B	100A-83B	1-1.5 MIN @ 72F	5-6 MIN @ 72F

*Cure time depends on temperate and relative humidity