

SPEEDSET SERIES	Physical Properties - Cured					Typical properties - Liquid							
	HARDNESS ASTM D 2240	TENSILE STRENGTH ASTM D 412	ELONGATION ASTM D412	TEAR STRENGTH ASTM D 624	COLOR	COMPONENT A*B*MIXED	VISCOSITY (CPS)	SPECIFIC GRAVITY	HAZARD	COMPONENT BY VOLUME	A*B MIXING BY WEIGHT	WORK LIFE	CURE TIME
	SPEEDSET 350	50-55 SHORE D	2800 PSI	250%	N/A	YELLOW	9.28 LB	600 CPS	1.1	NON-H	50A-100B	59A-100B	5-6 MIN @ 72F
SPEEDSET 371	60-70 SHORE D	2800 PSI	250%	N/A	CLEAR	9.19 LB	600 CPS	1.1	NON-H	50A-100B	59A-100B	3-6 MIN @ 72F	16-24 HR @ 72F
SPEEDSET 401	35-45 SHORE D	2800 PSI	200%	N/A	GRAY	9.26 LB	600 CPS	1.11	NON-H	1A-1B	100A-88B	3-6 MIN @ 72F	16-24 HR 2 72F
SPEEDSET 380	60-70 SHORE D	N/A	N/A	N/A	CLEAR	9.19 LB	600 CPS	1.1	NON-H	50A-100B	59A-100B	3-5 MIN @ 72F	24 HR @ 72F

*Cure time depends on temperate and relative humidity