

| TOP COAT SERIES | Physical Properties - Cured |                       |                          |                        |                       | Typical properties - Liquid |                    |                     |        |                        |                         |                 |              |
|-----------------|-----------------------------|-----------------------|--------------------------|------------------------|-----------------------|-----------------------------|--------------------|---------------------|--------|------------------------|-------------------------|-----------------|--------------|
|                 | HARDNESS<br>ASTM<br>D2240   | TENSILE ASTM D<br>412 | ELONGATION<br>ASTM D 412 | TEAR STRENGTH D<br>624 | COLOR                 | COMPONENT<br>A*B*MIXED      | VISCOSITY<br>(CPS) | SPECIFIC<br>GRAVITY | HAZARD | COMPONENT<br>BY VOLUME | A*B MIXING BY<br>WEIGHT | WORK LIFE       | CURE TIME    |
| TOPCOAT #6      | 70<br>SHORE A               | 4252 PSI              | 165%                     | 1103 LB/IN             | CLEAR                 | 7.97 LBS                    | 389 CPS            | 0.96                | HAZARD | 1A-1B                  | 100A-90.26B             | 30 MIN @ 72F    | 12 HRS @ 72F |
| TOPCOAT #7      | 75<br>SHORE A               | 3630 PSI              | 124%                     | 1025 LB/IN             | CLEAR                 | 8.37 BLS                    | 389 CPS            | 1                   | HAZARD | 1A-1B                  | 100A-97B                | 30 MIN @ 72F    | 12 HRS @ 72F |
| TOPCOAT #9      | 55<br>SHORE A               | 2846 PSI              | 207%                     | 496 LB/IN              | CLEAR                 | 8.30 LBS                    | 389 CPS            | 1                   | HAZARD | 1A-1B                  | 100A-97B                | 30 MIN @ 72F    | 12 HRS @ 72F |
| TOPCOAT CRX     | 75-85<br>SHORE A            | 2578 PSI              | 430%                     | 595 LB/IN              | CLEAR OR 19<br>COLORS | 7.67 LBS                    | 1340 CPS           | 0.92                | HAZARD | 100A-33B               | 100A-33.5B              | 45 MIN @<br>72F | 7 DAYS @ 75F |

\*Cure time depends on temperate and relative humidity