

RIGID MOLDING FOAM	PHYSICAL PROPERTIES-CURED					TYPICAL PROPERTIES-LIQUID							
	CLOSED CELL CONTENT ASTM 2856	SHRINKAGE ASTM D-2566	COMPRESS STENGTH	TEAR STRENGTH ASTM 624	COLOR	COMPONENT A*B*MIXED	VISCOSITY (CPS)	SPECIFIC GRAVITY	HAZARD	COMPONENT BY VOLUME	A*B MIXING BY WEIGHT	WORK LIFE	CURE TIME
3 LB DENSITY	95%	0.015	47.00	600 LB/IN	LT YELLOW	9.569 LB	650 CPS	1.15	NON-H	100A-100B	100A- 86.79B	30-60 SEC @ 72F	1-2 MIN @ 72F
*Cure time depends on temperate and relative humidity													