



<p>DESCRIPTION</p>	<p>InstaGel 30 is a two component Urethane elastomer that is specifically formulated as a brush on molding compound. After mixing, InstaGel 30 thickens to a creamy butterable gel that can easily be brushed on to vertical or overhead surfaces without sagging or running. In 24-hours InstaGel 30 cures to a tough rubber mold and is ready for use. InstaGel 30 is tough and has a high tear resistance as well as good grease and oil resistance. It has long mold storage life, insensitive inhibition and good adhesion between coats, as well as color coded for better mixing indication.</p>																																																												
<p>APPLICATION AND MIX RATIO</p>	<p>Component A and component B are supplied in 1 and 5 gallon plastic containers. Component B should be thoroughly mixed before using. Component A does not need mixing. Carefully measure out equal portions of component A and component B by volume in separate containers. Mix small batches by hand with a spatula. While mixing material carefully scrape down sides and bottom of container. Mixture gradually thickens over a 1 to 2 minute period to a creamy butterable consistency. Large batches should be avoided to insure even mixing. The ideal batch size is ½ gallon or less of total mix. It is important to mix correctly the exact amount of Part A to Part B to obtain maximum properties. Warmer temperature will decrease working life and cure time, whereas colder temperatures will increase the working life and cure time. InstaGel 30 can also be mix by weight: 100 parts of component A to 94 parts of component B by weight.</p>																																																												
<p>WORKING PROPERTIES</p>	<table border="0"> <tr> <td>Mix Ratio By weight</td> <td></td> <td>100 parts A/ 94 part B</td> </tr> <tr> <td>Mix Ratio By volume</td> <td></td> <td>100 parts A/ 100 parts B</td> </tr> <tr> <td>Viscosity @ 72°F (Mixed)</td> <td></td> <td>500,000 CPS</td> </tr> <tr> <td>Color</td> <td>Part A:</td> <td>Clear</td> </tr> <tr> <td>Color</td> <td>Part B:</td> <td>Light Green</td> </tr> <tr> <td>Color</td> <td>Mixed:</td> <td>Light Green</td> </tr> <tr> <td>Working Life @ 72°F</td> <td></td> <td>14-20 minutes</td> </tr> <tr> <td>Set Time* @ 72°F</td> <td></td> <td>24 hours</td> </tr> <tr> <td colspan="3">* Set time and Demold time depends on temperature and relative humidity.</td> </tr> <tr> <td>Specific Gravity: (Part A)</td> <td></td> <td>1.10</td> </tr> <tr> <td>Specific Gravity: (Part B)</td> <td></td> <td>1.04</td> </tr> <tr> <td>Specific Gravity: (Mixed)</td> <td></td> <td>1.07</td> </tr> <tr> <td>Weight/Gallon Part A</td> <td></td> <td>9.17 lbs.</td> </tr> <tr> <td>Weight/Gallon Part B</td> <td></td> <td>8.68 lbs.</td> </tr> <tr> <td>Weight/Gallon Mixed</td> <td></td> <td>8.93 lbs.</td> </tr> <tr> <td>Cubic inch per lb. of product</td> <td></td> <td>25.87</td> </tr> <tr> <td>Hardness @ 72° F</td> <td>ASTM 2240-85</td> <td>35-45 Shore A</td> </tr> <tr> <td>Tear Strength</td> <td>ASTM D-624</td> <td>230 lb./in.</td> </tr> <tr> <td>Tensile Strength</td> <td>ASTM D-412 die C</td> <td>1000 psi</td> </tr> <tr> <td>Elongation</td> <td>ASTM D-412 die C</td> <td>350%</td> </tr> </table>	Mix Ratio By weight		100 parts A/ 94 part B	Mix Ratio By volume		100 parts A/ 100 parts B	Viscosity @ 72°F (Mixed)		500,000 CPS	Color	Part A:	Clear	Color	Part B:	Light Green	Color	Mixed:	Light Green	Working Life @ 72°F		14-20 minutes	Set Time* @ 72°F		24 hours	* Set time and Demold time depends on temperature and relative humidity.			Specific Gravity: (Part A)		1.10	Specific Gravity: (Part B)		1.04	Specific Gravity: (Mixed)		1.07	Weight/Gallon Part A		9.17 lbs.	Weight/Gallon Part B		8.68 lbs.	Weight/Gallon Mixed		8.93 lbs.	Cubic inch per lb. of product		25.87	Hardness @ 72° F	ASTM 2240-85	35-45 Shore A	Tear Strength	ASTM D-624	230 lb./in.	Tensile Strength	ASTM D-412 die C	1000 psi	Elongation	ASTM D-412 die C	350%
Mix Ratio By weight		100 parts A/ 94 part B																																																											
Mix Ratio By volume		100 parts A/ 100 parts B																																																											
Viscosity @ 72°F (Mixed)		500,000 CPS																																																											
Color	Part A:	Clear																																																											
Color	Part B:	Light Green																																																											
Color	Mixed:	Light Green																																																											
Working Life @ 72°F		14-20 minutes																																																											
Set Time* @ 72°F		24 hours																																																											
* Set time and Demold time depends on temperature and relative humidity.																																																													
Specific Gravity: (Part A)		1.10																																																											
Specific Gravity: (Part B)		1.04																																																											
Specific Gravity: (Mixed)		1.07																																																											
Weight/Gallon Part A		9.17 lbs.																																																											
Weight/Gallon Part B		8.68 lbs.																																																											
Weight/Gallon Mixed		8.93 lbs.																																																											
Cubic inch per lb. of product		25.87																																																											
Hardness @ 72° F	ASTM 2240-85	35-45 Shore A																																																											
Tear Strength	ASTM D-624	230 lb./in.																																																											
Tensile Strength	ASTM D-412 die C	1000 psi																																																											
Elongation	ASTM D-412 die C	350%																																																											
<p>CLEAN UP</p>	<p>Dispose of all empty InstaGel 30 component containers in accordance with local, state and federal regulations. Empty component containers can be rendered non-hazardous by rinsing the containers with a small amount of mixed material and allowing material to cure for 24 hours. The containers will then contain non-hazardous cured urethane.</p>																																																												
<p>STORAGE AND SHELF LIFE</p>	<p>InstaGel 30 is shipped from the factory in sealed containers. The containers should be stored in a cool, dry area that is protected from direct sunlight and moisture. Storage temperatures should not exceed 80°F. The shelf life of the factory sealed containers stored under these conditions is six months. Containers that have been opened should be resealed immediately after material has been removed in order to prevent solvent evaporation.</p>																																																												
<p>SHIPPING CLASS</p>	<p>Class 55 Non-hazardous</p>																																																												