



DESCRIPTION	SpeedPak is two-component, light weight (0.75 lb/ft ³ density per cubic foot) urethane foam that is specifically formulated for pour-in-place packaging. It is water activated with easy mix by volume and variable cure speed. When mixed SpeedPak quickly rises to form lightweight semi-flexible foam that exactly contours to the part being packaged and adheres to the cardboard box. This enhances resistance to damage caused by impact and crushing caused during shipping. SpeedPak is a hand mixed system that requires no special equipment.																																	
WORKING PROPERTIES	<table border="0"> <tr> <td>Mix Ratio By weight</td> <td></td> <td>100 parts A / 83 parts B</td> </tr> <tr> <td>Mix Ratio By volume</td> <td></td> <td>100 parts A / 100 parts B</td> </tr> <tr> <td>Viscosity @ 72°F (A Side)</td> <td></td> <td>72 CPS</td> </tr> <tr> <td>Viscosity @ 72°F (B Side)</td> <td></td> <td>72 CPS</td> </tr> <tr> <td>Viscosity @ 72°F (Mixed)</td> <td></td> <td>72 CPS</td> </tr> <tr> <td>Color</td> <td>Part A:</td> <td>Clear Amber</td> </tr> <tr> <td>Color</td> <td>Part B:</td> <td>Clear Yellow</td> </tr> <tr> <td>Color</td> <td>Mixed:</td> <td>Rigid light yellow foam</td> </tr> <tr> <td>Working Life @ 72°F</td> <td></td> <td>1 – 1.5 minutes</td> </tr> <tr> <td>Demold Time* @ 72°F</td> <td></td> <td>5 – 6 minutes</td> </tr> <tr> <td>Complete Cure @ 72°F</td> <td></td> <td>5 – 6 minutes</td> </tr> </table> <p>* Set time and Demold time depends on temperature and relative humidity.</p>	Mix Ratio By weight		100 parts A / 83 parts B	Mix Ratio By volume		100 parts A / 100 parts B	Viscosity @ 72°F (A Side)		72 CPS	Viscosity @ 72°F (B Side)		72 CPS	Viscosity @ 72°F (Mixed)		72 CPS	Color	Part A:	Clear Amber	Color	Part B:	Clear Yellow	Color	Mixed:	Rigid light yellow foam	Working Life @ 72°F		1 – 1.5 minutes	Demold Time* @ 72°F		5 – 6 minutes	Complete Cure @ 72°F		5 – 6 minutes
Mix Ratio By weight		100 parts A / 83 parts B																																
Mix Ratio By volume		100 parts A / 100 parts B																																
Viscosity @ 72°F (A Side)		72 CPS																																
Viscosity @ 72°F (B Side)		72 CPS																																
Viscosity @ 72°F (Mixed)		72 CPS																																
Color	Part A:	Clear Amber																																
Color	Part B:	Clear Yellow																																
Color	Mixed:	Rigid light yellow foam																																
Working Life @ 72°F		1 – 1.5 minutes																																
Demold Time* @ 72°F		5 – 6 minutes																																
Complete Cure @ 72°F		5 – 6 minutes																																
PHYSICAL PROPERTIES	<table border="0"> <tr> <td>Specific Gravity: (Part A)</td> <td>1.16</td> </tr> <tr> <td>Specific Gravity: (Part B)</td> <td>0.97</td> </tr> <tr> <td>Specific Gravity: (Mixed)</td> <td>1.13</td> </tr> <tr> <td>Weight/Gallon Part A</td> <td>9.71 lbs.</td> </tr> <tr> <td>Weight/Gallon Part B</td> <td>8.06 lbs.</td> </tr> <tr> <td>Weight/Gallon Mixed</td> <td>8.88 lbs.</td> </tr> <tr> <td>Cubic inch per lb. of product</td> <td>23.04 in³</td> </tr> </table>	Specific Gravity: (Part A)	1.16	Specific Gravity: (Part B)	0.97	Specific Gravity: (Mixed)	1.13	Weight/Gallon Part A	9.71 lbs.	Weight/Gallon Part B	8.06 lbs.	Weight/Gallon Mixed	8.88 lbs.	Cubic inch per lb. of product	23.04 in ³																			
Specific Gravity: (Part A)	1.16																																	
Specific Gravity: (Part B)	0.97																																	
Specific Gravity: (Mixed)	1.13																																	
Weight/Gallon Part A	9.71 lbs.																																	
Weight/Gallon Part B	8.06 lbs.																																	
Weight/Gallon Mixed	8.88 lbs.																																	
Cubic inch per lb. of product	23.04 in ³																																	
CLEAN UP	Dispose of all empty SpeedPak component containers in accordance with local, state and federal regulations. Empty component containers can be rendered non-hazardous by rinsing the containers with a small amount of mixed material and allowing the solvents to evaporate. The containers will then contain non-hazardous cured urethane.																																	
STORAGE AND SHELF LIFE	SpeedPak is shipped from the factory in sealed containers. The containers should be stored in a cool, dry area that is protected from direct sunlight and moisture. Storage temperatures should not exceed 80° F. The shelf life of factory sealed containers stored under these conditions is six months. Containers that have been opened should be resealed immediately after material has been removed in order to prevent solvent evaporation.																																	
SHIPPING CLASS	Class 55 Non-hazardous																																	