



<b>DESCRIPTION</b>	<p>TrueCast 65 is a versatile two component liquid castable polyurethane elastomer. TrueCast 65 combines high strength and elongation with excellent chemical resistance to create durable flexible molds or parts. It is insensitive to typical environmental moisture, has high strength and low viscosity. Some features for TrueCast 65 include good grease and oil resistance, good flow into fine detail, good dimensional stability and good adhesion between pours. It is also tough, with high tear strength and insensitive to inhibition.</p>																																											
<b>APPLICATION AND MIX RATIO</b>	<p>Component A and component B are supplied in 1 and 5 gallon plastic containers. Component B should be thoroughly mixed before using. Component A does not need mixing. Carefully weigh out equal portions of component A and component B. Mix together for 1 to 2 minutes by hand using a spatula for small batches (1/2 gallon or less), or electric drill and jiffy mixer for larger batches. Use silicone mold release, even when using a silicone mold to avoid residual tack. Molds may be dusted with talc powder before pouring in liquid to produce a tack free permanent surface on cured parts. TrueCast 65 is fully cured in 24 hours at 72°F. Colder curing temperatures will lengthen cure times. Warmer temperatures will greatly reduce working and cure times. Curing can be heat accelerated (150°F/ 8 hours) to speed up processing. Use methyl ethyl ketone (MEK), acetone or mineral spirits for clean-up.</p>																																											
<b>WORKING PROPERTIES</b>	<table border="0"> <tr> <td>Mix Ratio By weight</td> <td></td> <td>100 parts A/ 100 part B</td> </tr> <tr> <td>Mix Ratio By volume</td> <td></td> <td>100 parts A/ 98 parts B</td> </tr> <tr> <td>Viscosity @ 72°F (A Side)</td> <td>Brookfield DV-II Pro #2 spindle at 3 rpm</td> <td>2550 – 2850 CPS</td> </tr> <tr> <td>Viscosity @ 72°F (B Side)</td> <td>Brookfield DV-II Pro #2 spindle at 3 rpm</td> <td>1900 – 2100 CPS</td> </tr> <tr> <td>Viscosity @ 72°F (Mixed)</td> <td>Brookfield DV-II Pro #2 spindle at 3 rpm</td> <td>2150 – 2450 CPS</td> </tr> <tr> <td>Color</td> <td>Part A:</td> <td>Clear</td> </tr> <tr> <td>Color</td> <td>Part B:</td> <td>Light Beige</td> </tr> <tr> <td>Color</td> <td>Mixed:</td> <td>Light Beige</td> </tr> <tr> <td>Working Life @ 72°F</td> <td>Gardco Standard Gel Timer (Model # GT-S)</td> <td>9-14 minutes</td> </tr> <tr> <td>Full Cure Time* @ 72°F</td> <td></td> <td>24 hours</td> </tr> </table> <p style="text-align: center;">* Set time and Demold time depends on temperature and relative humidity.</p>		Mix Ratio By weight		100 parts A/ 100 part B	Mix Ratio By volume		100 parts A/ 98 parts B	Viscosity @ 72°F (A Side)	Brookfield DV-II Pro #2 spindle at 3 rpm	2550 – 2850 CPS	Viscosity @ 72°F (B Side)	Brookfield DV-II Pro #2 spindle at 3 rpm	1900 – 2100 CPS	Viscosity @ 72°F (Mixed)	Brookfield DV-II Pro #2 spindle at 3 rpm	2150 – 2450 CPS	Color	Part A:	Clear	Color	Part B:	Light Beige	Color	Mixed:	Light Beige	Working Life @ 72°F	Gardco Standard Gel Timer (Model # GT-S)	9-14 minutes	Full Cure Time* @ 72°F		24 hours												
Mix Ratio By weight		100 parts A/ 100 part B																																										
Mix Ratio By volume		100 parts A/ 98 parts B																																										
Viscosity @ 72°F (A Side)	Brookfield DV-II Pro #2 spindle at 3 rpm	2550 – 2850 CPS																																										
Viscosity @ 72°F (B Side)	Brookfield DV-II Pro #2 spindle at 3 rpm	1900 – 2100 CPS																																										
Viscosity @ 72°F (Mixed)	Brookfield DV-II Pro #2 spindle at 3 rpm	2150 – 2450 CPS																																										
Color	Part A:	Clear																																										
Color	Part B:	Light Beige																																										
Color	Mixed:	Light Beige																																										
Working Life @ 72°F	Gardco Standard Gel Timer (Model # GT-S)	9-14 minutes																																										
Full Cure Time* @ 72°F		24 hours																																										
<b>PHYSICAL PROPERTIES</b>	<table border="0"> <tr> <td>Specific Gravity: (Part A)</td> <td></td> <td>1.03</td> </tr> <tr> <td>Specific Gravity: (Part B)</td> <td></td> <td>1.05</td> </tr> <tr> <td>Specific Gravity: (Mixed)</td> <td></td> <td>1.04</td> </tr> <tr> <td>Weight/Gallon Part A</td> <td>ASTM-D-1475</td> <td>8.63 lbs.</td> </tr> <tr> <td>Weight/Gallon Part B</td> <td>ASTM-D-1475</td> <td>8.74 lbs.</td> </tr> <tr> <td>Weight/Gallon Mixed</td> <td>ASTM-D-1475</td> <td>8.69 lbs.</td> </tr> <tr> <td>Cubic inch per lb. of product</td> <td></td> <td>26.19 in<sup>3</sup>/lb.</td> </tr> <tr> <td>Hardness @ 72° F</td> <td>ASTM 2240-85</td> <td>55-65 Shore A</td> </tr> <tr> <td>Tear Strength</td> <td>ASTM D-624</td> <td>375 lb./in.</td> </tr> <tr> <td>Tensile Strength</td> <td>ASTM D-412 die C</td> <td>1700 psi</td> </tr> <tr> <td>Elongation</td> <td>ASTM D-412 die C</td> <td>480%</td> </tr> <tr> <td>Modulus (100%)</td> <td>ASTM D-412 die C</td> <td>437 psi</td> </tr> <tr> <td>Modulus (200%)</td> <td>ASTM D-412 die C</td> <td>675 psi</td> </tr> <tr> <td>Modulus (300%)</td> <td>ASTM D-412 die C</td> <td>960 psi</td> </tr> </table>		Specific Gravity: (Part A)		1.03	Specific Gravity: (Part B)		1.05	Specific Gravity: (Mixed)		1.04	Weight/Gallon Part A	ASTM-D-1475	8.63 lbs.	Weight/Gallon Part B	ASTM-D-1475	8.74 lbs.	Weight/Gallon Mixed	ASTM-D-1475	8.69 lbs.	Cubic inch per lb. of product		26.19 in <sup>3</sup> /lb.	Hardness @ 72° F	ASTM 2240-85	55-65 Shore A	Tear Strength	ASTM D-624	375 lb./in.	Tensile Strength	ASTM D-412 die C	1700 psi	Elongation	ASTM D-412 die C	480%	Modulus (100%)	ASTM D-412 die C	437 psi	Modulus (200%)	ASTM D-412 die C	675 psi	Modulus (300%)	ASTM D-412 die C	960 psi
Specific Gravity: (Part A)		1.03																																										
Specific Gravity: (Part B)		1.05																																										
Specific Gravity: (Mixed)		1.04																																										
Weight/Gallon Part A	ASTM-D-1475	8.63 lbs.																																										
Weight/Gallon Part B	ASTM-D-1475	8.74 lbs.																																										
Weight/Gallon Mixed	ASTM-D-1475	8.69 lbs.																																										
Cubic inch per lb. of product		26.19 in <sup>3</sup> /lb.																																										
Hardness @ 72° F	ASTM 2240-85	55-65 Shore A																																										
Tear Strength	ASTM D-624	375 lb./in.																																										
Tensile Strength	ASTM D-412 die C	1700 psi																																										
Elongation	ASTM D-412 die C	480%																																										
Modulus (100%)	ASTM D-412 die C	437 psi																																										
Modulus (200%)	ASTM D-412 die C	675 psi																																										
Modulus (300%)	ASTM D-412 die C	960 psi																																										
<b>CLEAN UP</b>	<p>Dispose of all empty TrueCast 65 component containers in accordance with local, state and federal regulations. Empty component containers can be rendered non-hazardous by rinsing the containers with a small amount of mixed material and allowing material to cure for 24 hours. The containers will then contain non-hazardous cured urethane.</p>																																											
<b>STORAGE AND SHELF LIFE</b>	<p>TrueCast 65 is shipped from the factory in sealed containers. The containers should be stored in a cool, dry area that is protected from direct sunlight and moisture. Storage temperatures should not exceed 80°F. The shelf life of the factory sealed containers stored under these conditions is six months. Containers that have been opened should be resealed immediately after material has been removed in order to prevent solvent evaporation.</p>																																											
<b>SHIPPING CLASS</b>	<p>Class 55 Non-hazardous</p>																																											