

ENCAPSULATE SERIES	Physical Properties - Cured					Typical properties - Liquid							
	HARDNESS ASTM	LINEAR SHRINKAGE IP-SA-100	DIELECTRIC CONSTANT ASTM D-150	DIELECTRIC STRENGTH ASTND-149	COLOR	COMPONENT A*B*MIXED	VISCOSITY (CPS)	SPECIFIC GRAVITY	CB/IN PER POUND PRODUCTS	COMPONENT BY VOLUME	A*B MIXING BY WEIGHT	WORK LIFE	CURE TIME
EC 39 FAST-RUBBER	75-85 SHORE A ASTM 2240	1.02%			BLACK	8.86 LBS	490 CPS	1.06	26.07	1A-4B	100A-28.26B	3 MIN @ 72F	24 HRS @ 72 F
EC 39 SLOW	70-80 SHORE A ASTM 2240	0.01%			BLACK	8.62 LBS	270 CPS	1.032	26.83	1 A-4 B	100A-25.83B	26 MIN @72 F	7 DAYS @ 72 F

*Cure time depends on temperate and relative humidity