

FIBERLOCK SERIES	Physical Properties - Cured					Typical properties - Liquid							
	HARDNESS ASTM D 2240	TENSILE STRENGTH ASTM D 412	ELONGATION ASTM D 412	TEAR STRENGTH ASTM D 624	COLOR	COMPONENT A*B*MIXED	VISCOSITY (CPS)	SPECIFIC GRAVITY	HAZARD	COMPONENT BY VOLUME	A*B MIXING BY WEIGHT	WORK LIFE	CURE
FIBERLOCK-100	65-75 SHORE A	400 PSI	250%	45 LB/IN	VARIOUS	7.63 LB	250 CPS	0.92	HAZARD	1 PART	1 PART	30 MIN @ 72F	24 HR @ 72F

*Cure time depends on temperate and relative humidity