

HYDROSPAN SERIES		Physical Properties - Cured					Typical properties - Liquid							
		HARDNESS ASTM 2240	EXPAND/REDUCE RATE	ELONGATION ASTM D412	TEAR STRENGTH ASTM 624	COLOR	COMPONENT A*B*MIXED	VISCOSITY (CPS)	SPECIFIC GRAVITY	HAZARD	COMPONENT BY VOLUME	A*B MIXING BY WEIGHT	WORK LIFE	CURE TIME
HYDROSPAN 100 (EXPANDING RESIN)	Softer ↑	40 SHORE A	+161%	100%		TRANS BLUE	8.96 LB	1200 CPS	1.07	NON-H	100A-54B	100A-50B	14-16 MIN @ 72F	24 HRS @ 72F
			-19%			WHITE	8.95 LB		1.07	NON-H	1 PART	1 PART	3-5 MIN @ 72F	30 MIN @ 72F
HYDROSPAN 400 (REDUCING RESIN)														

\*Cure time depends on temperate and relative humidity