

TRUEKOTE SERIES	Physical Properties - Cured							Typical properties - Liquid					
	HARDNESS ASTM D 2240	TENSILE STRENGTH ASTM D412	ELONGATION ASTM D 412	TEAR STRENGTH ASTM 412	COLOR	COMPONENT A*B*MIXED	VISCOSITY (CPS)	SPECIFIC GRAVITY	HAZARD	COMPONENT BY VOLUME	A*B MIXING BY WEIGHT	WORK LIFE	CURE TIME
CS-100	75-85 SHORE A	2850 PSI	450%	385 LB/IN	18 COLORS	8.63 LB	7500 CPS	1.03	NON-H	100A- 15.20B	100A- 16.12B	50-70 MIN @ 72F	7 DAYS @ 72F
CS-100FR (FIRE RESISTANT)	75-85 SHORE A	3200 PSI	350%	385 LB/IN	MED GRAY	8.72 LB	15000 CPS	1.05	NON-H	100A-18.1B	100A-22.9B	30-45 MIN @ 72F	7 DAYS @ 72F
CS-200 NON-SKID	65-75 SHORE A	N/A	N/A	N/A	CLEAR	14.12 LB	4200 CPS	1.69	HAZARD	51.81A- 100B	25.31A- 100B	30 MIN @ 72F	7 DAYS @ 72F
CS-150 SPRAYABLE	85-95 SHORE A	5240 PSI	490%	990 LB/IN	18 COLORS	8.10 LB	10000 CPS	0.97	HAZARD	100A- 33.33B	100A-32B	45 MIN @ 72F	24 HRS @ 72F
CS-155 S SPRAYABLE	85-95 SHORE A	4018 PSI	468%	829 LB/IN	CLEAR AMBER	8.16 LB	1900 CPS	0.98	HAZARD	100A-20B	100A- 19.74B	30-45 MIN @ 72F	7 DAYS @ 72F
CS-252 SPRAYABLE	75-80 SHORE A	4325 PSI	725%	563 LB/IN	BLACK	7.88 LB	350 CPS	0.95	HAZARD	100A-6.1297	100A-6.66B	30-45 MIN @ 72F	7 DAYS @ 72F

Softer ↑

*Cure time depends on the temperature and humidity