

URASEAL SERIES		Physical Properties - Cured				Typical properties - Liquid								
		HARDNESS ASTM 2240	TENSILE STRENGTH ASTM D 412	ELONGATION ASTM D 412	TEAR STRENGTH ASTM 2240	COLOR	COMPONENT A*B*MIXED	VISCOSITY (CPS)	SPECIFIC GRAVITY	HAZARD	COMPONENT BY VOLUME	A*B MIXING BY WEIGHT	WORK LIFE	CURE TIME
URASEAL 100	Softer ↑↓	50 SHORE A	550 PSI	300%	139 LB/IN	GRAY	9 LBS	2600 CPS	1.08	NON-H	1A-1B	N/A	20 MIN @ 72F	24 HRS @ 72F
URASEAL 210		25-35 SHORE A	604 PSI	660%	139 LB/IN	LT GRAY	8.34 LBS	1500 CPS	1.08	NON-H	1A-1B	100A-96B	15 MIN @ 72F	24 HRS @ 72F

*Cure time depends on temperate and relative humidity